



Technical Data Sheet

UV-Resistant Cable Ties

Worldwide

cannot be reopened

CHARACTERISTICS OF MATERIALS USED

	POLYAMIDE 6.6 BLACK UV stabilized Suitable for outdoor applications.
Humidity absorption: Temperature range Working temperature: Tightening temperature: Max. admissible point: Melting temperature: Limiting Oxygen Index (LOI): Corrosion in case of smoke: Flammability rating: Dielectric strength:	2.7 % (23 °C – 50 % relative humidity) –40 °C to +105 °C –10 °C to +60 °C +110 °C for short time +256 °C 27 % 5 % UL 94-V2 50,000 volts/mm
Resistance against chemicals:	Excellent resistance to aromatic solvents, oils, greases and derivates. Good resistance to bases. Limited resistance to acids. Not resistant to phenols and chlorinated solvents. Halogen free
UV resistance:	The special compound assures an UV resistance according to CEI EN 62275 § 6.2.2 – Type 2: retains 100 % strength after testing (ISO 4892-2 method A – 1000 h equivalent to 10 years of outdoor exposure) xenon-arc radiation.

Certificates: UL (Underwriters Laboratories): File E 86244
DNV-GL (Det Norske Veritas and Germanischer Lloyd): TAE00001DU

Raw material used to produce cable ties comply with EC Directives: 2000/53/EC (ELV), 2012/19/EC (WEEE), 2003/11/EC

Products are tested according to EN IEC 62275 “Cable ties for Electrical Installation”.

Recommendation: Keep bag closed after use.

Württembergische Allplastik GmbH
Johannes-Kepler-Str. 12
71083 Herrenberg, Germany
Tel: +49 7032 9368 0
Fax: +49 7032 9368 98

www.allplastik.com
info@allplastik.com

Certified according to ISO 9001:2015